

PETRONAS GREASE CLAY MEP

High Temperature Organophilic Bentonite Grease with Solid Lubricant

PETRONAS Grease CLAY MEP is a high temperature Organophilic Bentonite grease with solid lubricant specially developed for industrial equipment where the capability of conventional greases may be exceeded by either continuous high temperature or cyclic conditions ranging from normal to extremely high temperatures.

Formulated with selected mineral base oils enhanced with Organophilic Bentonite clay thickened, advanced anti-oxidant, anti-rust, Molybdenum Disulphide, and corrosion inhibitor additives. PETRONAS Grease CLAY MEP provides excellent high temperature performance and high shock load capabilities.

PETRONAS Grease CLAY MEP meets or exceeds key industrial specifications.

Applications

PETRONAS Grease CLAY MEP is recommended for use in:

- lubrication of plain and anti-friction bearings operating continuously between 150°C to 170°C range or under conditions where bearings are repeatedly cycled from normal ambient temperatures to high operating temperatures
- equipment such as oven conveyors chain bearings, kiln car wheel bearings and paper mill driers and corrugators
- glass manufacture conveyer belt roller bearings, cams and slideways

Note: PETRONAS Grease CLAY MEP is recommended for operating temperature range of -20°C to +140°C (Max. +180°C).

PETRONAS GREASE CLAY MEP

High Temperature Organophilic Bentonite Grease with Solid Lubricant

Features and Benefits

Features	Benefits
Very good pumpability	Very good performance where low temperature performance is required
Excellent anti-wear protection	Protects equipment components from excessive wear at high temperatures and provides long equipment life
Excellent load carrying capacity	Contains special additives which enables the grease to withstand heavy loads without losing the lubricant film
Friction reduction capabilities	Has friction reducing solid additives for extra protection on sliding metal surfaces
High rust & corrosion protection	Protects bearing surfaces against rust and corrosion, even when the grease is contaminated with water
High resistance to water and steam wash-out	Equipment protection and good lubrication even in presence of water or steam
High thermal and oxidation stability	Has good oxidation resistance and can withstand high operating temperatures without hardening or forming bearing deposits
High oil bleed control	Has a high controlled oil bleed and does not separate under storage

PETRONAS GREASE CLAY MEP

High Temperature Organophilic Bentonite Grease with Solid Lubricant

Typical Properties

Characteristic	Method	Specification	CLAY MEP
Thickener Type	-	Clay	Clay
NLGI	ASTM D217	1	1
Color	Visual	Grey	Grey
Worked Penetration, mm/10	ASTM D217	310 - 340	325
Worked Penetration 100.000x, Penetration Change, mm/10, Max.	ASTM D217	+20	+18
Oil Separation, Mass %, Max.	ASTM D1742	6	5
Dropping Point, °C, Min.	ASTM D2265	Non-Melt	Non-Melt
Four Ball Wear, mm, Max.	ASTM D2266	0,50	0,50
Four Ball EP Weld Point, Min.	ASTM D2596	200	200
Flow Pressure at -20°C, mbar, Max.	DIN 51805 mod	1400	<1400
SKF R2F B at 140°C	SKF	Pass	Pass
Roll Stability, % of Penetration Change, Max.	ASTM D1831	20	10
Water Washout at 38°C, %, Max.	ASTM D1264	10	5
Water Resistance at 90°C, %, Max.	DIN 51807:1	3	1
Emcor Test (Salt Water), Max.	ASTM D6138	1-1	0-0
Base Oil Viscosity @40°C, cSt	ASTM D445	450 - 470	460
Molybdenum Disulfide, Mass %	-	1	1

All technical data are provided for reference only / SS is available upon request including quality control limits

Performance Levels

- DIN 51502 KF1N-20
- ISO 12924 L-XB(F)DAA1

PETRONAS GREASE CLAY MEP

High Temperature Organophilic Bentonite Grease with Solid Lubricant

Health, Safety and Environment

This product is unlikely to present any significant health and safety hazards when used in the recommended application. Avoid contact with skin. Wash immediately with soap and water after skin contact. Do not discharge into drains, soil or water.

For further detail regarding storage, safe handling, and disposal of product, please refer to product SDS or contact us at: www.pli-petronas.com.

Important Note

The word PETRONAS, the PETRONAS logo and such other related trademarks and/or marks used herein are trademarks or registered trademarks of PETRONAS Lubricants International Sdn. Bhd. ("PLISB"), or its subsidiaries or related Holding Corporation under license unless indicated otherwise. The PLI Documents and the information contained herein are believed to be accurate as of the date of printing. PLISB makes no express or implied representation or warranties as to its accuracy or completeness or information in or any transaction performed. The PLI Documents and information provided are based on standard tests under laboratory conditions and is given only as a guide. Users are advised to ensure that they refer to the latest version of these PLI Documents. It is the responsibility of the users to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations imposed by the respective local authorities.

Safety Data Sheets are available for all our products and should only be consulted for appropriate information regarding storage, safe handling and disposal of the product. No responsibility shall be taken by either PLISB or its subsidiaries and related holding corporation for any loss or injury or any direct, indirect, special, exemplary, consequential damages or any damages whatsoever, whether in action of contract, negligence or other tortuous action, in connection with or resulting from abnormal use of the materials and/or information, from any failure to adhere to recommendations, or from hazards inherent in the nature of the materials and/or information. All products, services and information supplied are under our standard conditions of sale. Please consult with any of our local representatives in the event you require any further information.