

PETRONAS GREASE LiCa GEP 2.5

Extreme Pressure Lithium Calcium Grease

PETRONAS Grease LiCa GEP 2.5 is an extreme pressure Lithium Calcium grease with solid additives specially developed for lubrication of open gears, racks, chains, wire ropes, support rollers, slides and sprockets.

Formulated with selected mineral base oils enhanced with functional polymer and thickened Lithium Calcium soap, advanced extreme pressure, anti-oxidant, anti-rust and corrosion inhibitors additives. PETRONAS Grease LiCa GEP 2.5 provides excellent load carrying protection, water washout, spray off resistance and long life in applications operating at elevated temperatures.

PETRONAS Grease LiCa GEP 2.5 meets or exceeds key industrial specifications.

Applications

PETRONAS Grease LiCa GEP 2.5 is recommended for use in:

- open gears, racks, chains, wire ropes, support rollers, tracks, slides and sprockets
- steel, cement, paper, chemical, mining, and other industries requiring heavy duty lubrication
- fifth wheel lubrication in the automotive industry
- rough plain bearings, slides, conveyor chains, and bearings of boiler soot-blowers

Note: PETRONAS Grease LiCa GEP 2.5 is recommended for operating temperature range of -20°C to +120°C (Max. +130°C).

Features and Benefits

Features	Benefits
Excellent pumpability	Excellent performance where low temperature performance is required
Excellent load carrying capacity	Contain special EP additives which enable the grease to withstand heavy shock loads without losing the lubricant film
High rust & corrosion protection	Protect metal surfaces against corrosion, even when the grease is contaminated with water
High resistance to water wash-out	Equipment protection and good lubrication even in presence of water
High friction reduction capabilities	Has friction reducing additives for extra protection on sliding metal surfaces

PETRONAS GREASE LiCa GEP 2.5

Extreme Pressure Lithium Calcium Grease

Typical Properties

Characteristic	Method	Specification	LiCa GEP 2.5
Thickener Type	-	Lithium Calcium	Lithium Calcium
NLGI	ASTM D217	2.5	2.5
Color	Visual	Dark Grey	Dark Grey
Worked Penetration, mm/10	ASTM D217	245 - 275	265
Worked Penetration 100.000x, Penetration Change, mm/10, Max.	ASTM D217	+25	+20
Oil Separation, Mass %, Max.	ASTM D1742	6	3
Dropping Point, °C, Min.	ASTM D2265	180	190
Four Ball Wear, mm, Max.	ASTM D2266	0,50	0,40
Four Ball EP Weld Point, Min.	ASTM D2596	400	400
SKF R2F B at 120°C	SKF	Pass	Pass
Flow Pressure at -20°C, mbar, Max.	DIN 51805 mod	1400	<1400
Roll Stability, % of Penetration Change, Max.	ASTM D1831	10	8
Wheel Bearing Leakage, grams, Max.	ASTM D4290	10	8
Water resistance at 90°C, Max.	DIN 51807:1	3	1
Water Washout at 38°C, %, Max.	ASTM D1264	10	8
Rust Protection, rating	ASTM D1743	Pass	Pass
Emcor Test (Salt Water), Max.	ASTM D6138	1-1	0-0
Base Oil Viscosity @40°C, cSt	ASTM D445	490 - 510	500
Graphite, Mass %	-	10	10

All technical data are provided for reference only / SS is available upon request including quality control limits

Performance Levels

- DIN 51502 OGP2.5K-20
- ISO 12924 L-XB(F)CIB2.5

PETRONAS GREASE LiCa GEP 2.5

Extreme Pressure Lithium Calcium Grease

Health, Safety and Environment

This product is unlikely to present any significant health and safety hazards when used in the recommended application. Avoid contact with skin. Wash immediately with soap and water after skin contact. Do not discharge into drains, soil or water.

For further detail regarding storage, safe handling, and disposal of product, please refer to product SDS or contact us at: www.pli-petronas.com.

Important Note

The word PETRONAS, the PETRONAS logo and such other related trademarks and/or marks used herein are trademarks or registered trademarks of PETRONAS Lubricants International Sdn. Bhd. ("PLISB"), or its subsidiaries or related Holding Corporation under license unless indicated otherwise. The PLI Documents and the information contained herein are believed to be accurate as of the date of printing. PLISB makes no express or implied representation or warranties as to its accuracy or completeness or information in or any transaction performed. The PLI Documents and information provided are based on standard tests under laboratory conditions and is given only as a guide. Users are advised to ensure that they refer to the latest version of these PLI Documents. It is the responsibility of the users to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations imposed by the respective local authorities.

Safety Data Sheets are available for all our products and should only be consulted for appropriate information regarding storage, safe handling and disposal of the product. No responsibility shall be taken by either PLISB or its subsidiaries and related holding corporation for any loss or injury or any direct, indirect, special, exemplary, consequential damages or any damages whatsoever, whether in action of contract, negligence or other tortuous action, in connection with or resulting from abnormal use of the materials and/or information, from any failure to adhere to recommendations, or from hazards inherent in the nature of the materials and/or information. All products, services and information supplied are under our standard conditions of sale. Please consult with any of our local representatives in the event you require any further information.